# Bacterial Leakage in Roots Filled With Different Medicaments and Sealed With Cavit

Claudia R. Barthel, PD, Dr. med. dent,\* Felix F. Zaritzki, Dr. med. dent.,<sup>†</sup> Wolfgang H.-M. Raab, Prof. Dr. med. dent.,\* and Stefan Zimmer, Prof. Dr. med. dent.\*

#### **Abstract**

The aim of this study was to evaluate the time required by four different root canal medications coupled with the temporary filling material Cavit (ESPE, Seefeld, Germany) to prevent penetration of bacteria into the root canal. There were 145 roots prepared in a standardized manner. Four groups with 15 samples each were dressed with calcium hydroxide (Ca(OH)<sub>2</sub>), a 5% chlorhexidine gel (CHX), a chloromono-campherphenolic compound (ChKM), and Ledermix (LM), respectively, and sealed with Cavit. Four control groups contained identical medications but the roots were left unsealed. The 25 remaining roots served as additional controls. A standard setup for bacterial leakage studies was chosen with Staphylococcus epidermidis as test strain. Cavit application resulted in a significantly better seal compared with the unsealed groups. In the Cavit-sealed groups, all groups differed significantly from one another except for the CHX and the ChKM groups. The Ca(OH), medicated roots provided the longest protection (median of 36 days), followed by the Ledermixgroup (27 days) and the CHX (18 days) or ChKM groups (19 days). It may be concluded that Cavit-sealed and medicated root canals do not provide adequate protection against bacterial leakage for more than 1 month. (J Endod 2006;32:127-129)

### **Key Words**

Bacterial penetration, calcium hydroxide, cavit, chlorhexidine, ledermix, phenolic derivative, temporary medication

From the \*Department of Operative and Preventive Dentistry and Endodontics, Heinrich-Heine-University, Duesseldorf, Germany; †Private Practice, Berlin, Germany.

Address requests for reprints to Dr. Claudia R. Barthel, Building 18. 13, Department of Operative and Preventive Dentistry and Endodontics, Heinrich-Heine-University, Moorenstr. 24, D-40225 Duesseldorf, Germany. E-mail address: claudia.barthel@med.uni-duesseldorf.de.

0099-2399/\$0 - see front matter

Copyright © 2006 by the American Association of Endodontists.

doi:10.1016/j.joen.2005.10.023

Periapical inflammation is mainly associated with the presence of bacteria in the apical environment (1,2). Thus, in infected cases removal of microorganisms from the root canal system is mandatory. To a certain extent, this can be achieved by chemomechanical debridement (3,4). In some cases it may be necessary to additionally provide the root canal with dressings to enhance the bactericidal effect. Several substances, such as calcium-hydroxide  $(Ca(OH)_2)$ , compounds of antibiotics and corticoids, phenolic derivatives, or chlorhexidine (CHX), have been proposed to serve this purpose.

The antibacterial effect of  ${\rm Ca(OH)}_2$  is attributed chiefly to its high pH. However, to gain adequate alkalization of the entire root it needs to be applied for a minimum period of 1 to 2 weeks (5,6). Application of the antibiotic-corticoid compound Ledermix (Lederle, Wolfratshausen, Germany) is recommended for 2 to 12 weeks (7,8). Therefore, it may be necessary to leave a temporary medication, either in order for it to develop its antibacterial activity or for reasons of patient management, for several weeks in the root canal system.

Roach et al. examined the duration of bacterial passage through temporarily dressed root canals without coronal seal (9). Different  $\text{Ca}(\text{OH})_2$ -and CHX-formulations were used. The  $\text{Ca}(\text{OH})_2$ -paste groups exhibited a significantly superior protection against bacterial penetration than the CHX group and the group with  $\text{Ca}(\text{OH})_2$ -points. The samples were, however, tested without a coronal seal, which is usually not performed during a clinical endodontic procedure.

Cavit (ESPE, Seefeld, Germany) is often used as temporary coronal seal for root canals. However, it does not provide a satisfactory coronal seal in root filled teeth against bacterial penetration (10, 11). Whether the combination of Cavit coupled with different intracanal dressings is capable of providing an adequate seal for extended time periods has till date not been investigated.

The aim of this study was to evaluate how long medicated and Cavit-sealed roots were effective in preventing bacterial leakage. As intracanal dressings Ca(OH)<sub>2</sub>, Ledermix paste, a camphorated mono-chloro-phenolic compound or a chlorhexidine gel were to be used.

## **Materials and Methods**

There were 145 human maxillary canines used for this experiment. After separation of the crown, the roots were coronally ground to a uniform length of 16 mm. Standardized cavities, mimicing clinical access cavities, 5 mm in depth and 2.5 mm in diameter were drilled into the coronal parts of the roots. The canals were instrumented to an ISO #60 file at 15 mm length while being irrigated with copious amounts of 2.5% NaOCl. The apical opening was standardized by placing an ISO #30 instrument 1 mm beyond the apex. The smear layer was removed with a 2-minute rinse of 15% EDTA followed by a final flush of NaOCl. The roots were randomly assigned to four test groups with 15 samples each and seven control groups, five of them with 15 samples and two with five samples each.

All roots were sterilized in ethylene-oxide and furtheron treated under sterile conditions. In test groups 1 to 4, the root canals were filled with four different temporary dressings: Group 1 (Ca(OH)<sub>2</sub>/Cav) received a fresh mix of Ca(OH)<sub>2</sub>, group 2 (LM/Cav) Ledermix paste (Lederle, Wolfratshausen, Germany), group 3 (CHX/Cav) an experimental 5% CHX-methylcellulose gel, and in group 4 (ChKM/Cav), a cotton pellet soaked in a campher monochlorophenolic compound with an additive of menthol (Walkhoff's

# **Basic Research—Technology**

ChKM: Haupt, Würzburg, Germany) was placed in the access cavity. All test groups were provided with a small cotton pellet at the canal orifics and coronally sealed with Cavit. Control groups 5 to 8 (Ca(OH)<sub>2</sub>, LM, CHX and ChKM) were each filled with the same medication as in the experimental groups and a small cotton pellet was inserted into the access cavity. The root canals were, however, left unsealed. There were 15 root canals sealed coronally with Cavit only. Five root canals were left empty and served as positive controls, whereas five other root canals were entirely covered with sticky wax, serving as negative controls.

The roots were placed between two chambers according to a former experimental setup described by Barthel et al. (11). The upper chamber contained a streptomycin resistant  $Staphylococcus\ epidermidis\ strain\ (1\times 10^8\ CFU/ml)$ , as test strain. To minimize the possibility of contamination, the lower chamber was filled with a sterile clear soy broth containing 0.125 mg/ml streptomycinsulfate. Occurrence of turbidity was checked on a daily basis. Turbidity in the lower chamber indicated a leaking root. Upon appearance of the turbidity, the sample was opened and vitality and conformity of bacteria with the upper chamber were checked by incubating fluid of both chambers on Columbia agar. The experiment was conducted until all samples except for the negative controls leaked.

After gathering the data, they were statistically confirmed as being nonparametric with the Kolgomorov-Smirnov test. The average day of leakage was determined for each group. The Kruskal Wallis test was applied to detect the presence of statistically significant differences among the groups. The single groups were tested against one another by employing the Mann-Whitney U test. In addition, every week the cumulative number of leaking samples was recorded per group. The  $\chi^2$  test was calculated to detect significant differences for the number of leaking samples per week and group. The level of significance was set at p < 0.05.

# **Results**


The experiment was terminated after 6 weeks. By then, all samples except for the negative controls had leaked. Positive (empty) controls leaked after 1 day. All turbid bottom chambers were bacteria-positive with *S. epidermidis*. The number of leaking samples per group and the first and last day of leakage can be seen in Table 1.

All groups differed significantly from one another with regard to the mean day of leakage in the test groups, except for the CHX/Cav and the ChKM/Cav groups. Ca(OH)<sub>2</sub>/Cav showed the longest protection followed by LM/Cav and CHX/Cav or ChKM/Cav. The same statistical sig-

**TABLE 1.** Days of leakage per group

Dressing	Test Groups Leaking Between Day	Median Day of Leakage
Ca (OH) <sub>2</sub> /Cav	27 and 47	36
LM/Cav ¯	20 and 37	27
ChKM/Cavit	10 and 21	n.s. [ 19 18
CHX/Cavit	11 and 21	n.s. [ 18
•		

	Dressing	Control Groups Leaking Between Day	Median Day of Leakage
Ī	Ca (OH) <sub>2</sub>	12 and 24	19
	Ledermix	1 and 20	14
	ChKM	All on day 1	n 1
	CHX	All on day 1	n.s. $\begin{bmatrix} & \cdot \\ & 1 \end{bmatrix}$
	Cavit	10 and 20	17
	Positive Controls	All on day 1	1
	Negative Controls	No leakage	0




**Figure 1.** Unsealed (control) samples: number of leaking samples per group, cumulative values per week.

nificances applied to the unsealed control groups, in which, once again, the  $Ca(OH)_2$  samples showed longest protection. In general, Cavit application resulted in a significantly better seal when comparing the unsealed with the sealed groups.

The cumulative numbers of leaking samples per week can be seen in Figs. 1 and 2. In the sealed and medicated groups, Ca(OH)<sub>2</sub>/Cav and LM/Cav showed significantly fewer leaking samples in week 3 compared to the CHX/Cav and the ChKM/Cav groups. In weeks 4 and 5 Ca(OH)<sub>2</sub>/Cav was significantly superior to the two aforementioned groups. In unsealed groups, Ca(OH)<sub>2</sub> and LM groups showed significantly fewer leaking samples during the first 2 weeks when compared to the other two groups. Besides the above-mentioned no significant differences in the number of leaking samples was observed.

# **Discussion**

Intracanal dressings may be applied to support chemo-mechanical debridement (12, 13). When administered because of lack of time



**Figure 2.** Coronally sealed samples: number of leaking samples per group, cumulative values per week.

during endodontic treatment they serve to occupy root canal space and therefore do not leave room for bacterial multiplication (14). Depending on the individual treatment protocol, medications may be applied for days, weeks, or in case of apexogenesis even months. Hence, besides disinfection, it is necessary for the medications to maintain an environment low in bacterial count. In the present study, Ca(OH), has been used as standard medication. According to a recent meta-analysis it has been designated as the best root canal medication available (15). As CHX has often been discussed as a replacement or adjunct medication it was added to the study protocol (16, 17). Because Ledermix is frequently used in Europe and Australia it was also incorporated into the study. Finally, owing to its popularity in private practices, although it has been proven to be inferior to Ca(OH)<sub>2</sub> in an in vivo study by Byström et al. (12), chloromono-campherphenolic compound was also included in the study. The exact formula of the presently used Walkhoff solution (ChKM) was slightly different from the one used by Byström et al. in their study. It contained 217 mg/g 4-chlorophenol, 712 mg/g camphor, and 17 mg/g menthol in alcohol. The solution used in the Byström study (CMCP) contained 30% monochlorophenol, 60% camphor, and 10% alcohol. Whether this difference in formulation has a significant impact on the outcome of disinfection has not yet been proven.

All intracanal dressings were applied with a lentulo spiral, except for ChKM, which has a much lower viscosity. Hence, a cotton pellet was soaked in the volatile solution and placed in the cavity, thereby negating its function of occupying the root canal space to suppress bacterial multiplication. This, in addition to it being highly volatile could give reason for its inferior performance in this study. Studies show that one day after application of CMCP, only up to 10% of it remains in the root canal system (18–20). This result may be similar with the ChKM solution.

CHX is known to have a good antibacterial effect (21–23). However, in the present study the antibacterial protection attributed was similar to the one of ChKM. This may be a result of the fact that dentin reduces the disinfecting effect of CHX to a certain extent (24). Furthermore, a substantivity effect as discussed in earlier studies could not be confirmed by this study (25, 26).

The long-term antimicrobial effect of Ledermix has been questioned (27). In the present study it was found to be superior to CHX and ChKM in preventing bacterial intrusion. Ledermix does not set after application, however, it does create some kind of barrier by drying out. This barrier may be helpful in prolonging the protection. Additionally, only one strain of bacteria was tested in this study. It may be assumed that Ledermix has a very good antibacterial effect against this strain.

In former studies, Cavit has been shown to have a weak seal against bacterial penetration (10, 11). In this study, four groups were dressed with the medicaments and left unsealed as controls. The four test groups were coronally sealed. In this manner the sole effect of Cavit could be determined. By placing Cavit into the coronal cavity, average bacterial penetration could be prolonged for 13 to 18 days. This duration could have been increased by avoiding the use of cotton pellets underneath the Cavit filling. Even when placed with utmost care, it is inevitable to prevent extrusion of even tiniest cotton fibers from the cavity providing a pathway for bacteria into the root canal system. Prior knowledge of this drawback encouraged the authors to place the pellets as carefully as possible. This procedure was chosen because is a common practice rendering an easy access to the root canal in the following appointment.

It may be concluded that in terms of providing protection against bacterial penetration Ca(OH)<sub>2</sub> presents itself as the best root canal medication. Coronal seal with Cavit prolongs the protection significantly, nevertheless, an adequate seal cannot be provided for more than 1 month. Other coronal sealing materials such as glass-ionomer cement

or adhesively applied composite fillings may enhance the seal for longer time intervals. The camphorated monochlorophenolic compound showed the worst results.

# **Acknowledgment**

We would like to thank Dr. Preeti Singh for revising the manuscript.

# References

- Kakehashi S, Stanley H, Fitzgerald R. The effects of surgical exposures of dental pulps in germ-free and conventional laboratory rats. Oral Surg Oral Med Oral Pathol 1965;20:340-9.
- Sundqvist G. Bacteriologic studies of necrotic pulps. Thesis: University of Umeå; 1976.
- Byström A, Sundqvist G. Bacteriologic evaluation of the efficacy of mechanical root canal instrumentation in endodontic therapy. Scand J Dent Res 1981;89:321–9.
- Byström A, Sundqvist G. Bacteriologic evaluation of the effect of 0.5 percent sodium hypochlorite in endodontic therapy. Oral Surg Oral Med Oral Pathol 1983;55: 307–12.
- Nerwich A, Figdor D, Messer HH. pH changes in root dentin over a 4-week period following root canal dressing with calcium hydroxide. J Endod 1993;19:302–6.
- Sjögren U, Figdor D, Spångberg L, et al. The antimicrobial effect of calcium hydroxide as a short-term intracanal dressing. Int Endod J 1991;24:119 –25.
- Abbott PV. Medicaments: aids to success in endodontics. Part 2. Clinical recommendations. Aust Dent J 1990;35:491–6.
- Abbott PC, Hume WR, Pearmann JW. Antibiotics and endodontics. Aust Dent J 1990;35:50-60.
- Roach RP, Hatton JF, Gillespie MJ. Prevention of the ingress of a known virulent bacterium into the root canal system by intracanal medications. J Endod 2001;27:657–60.
- Barthel CR, Strobach A, Briedigkeit H, et al. Leakage in roots coronally sealed with different temporary fillings. J Endod 1999;25:731–4.
- Barthel CR, Zimmer S, Wussogk R, et al. Long-Term bacterial leakage along obturated roots restored with temporary and adhesive fillings. J Endod 2001;27:559 – 62.
- Byström A, Claesson R, Sundqvist G. The antibacterial effect of camphorated paramonochlorophenol, camphorated phenol and calcium hydroxide in the treatment of infected root canals. Endod Dent Traumatol 1985;1:170-5.
- Shuping G, Ørstavik D, Sigurdsson A, et al. Reduction of intracanal bacteria using Nickel-Titanium rotary instrumentation and various medicaments. J Endod 1999;26:751–5.
- Peters LB, Wesselink PR, van Winkelhoff AJ. Combinations of bacterial species in endodontic infections. Int Endod J 2002;35:698-702.
- Law A, Messer HH. An evidence-based analysis of the effectiveness of intracanal medicaments. J Endod 2004;30:689

  –94.
- Komorowski R, Grad H, Wu XY, et al. Antimicrobial substantivity of chlorhexidinetreated bovine root dentin. J Endod 2000;26:315

  –7.
- Lenet BJ, Komorowski R, Wu XY, et al. Antimicrobial substantivity of bovine root dentin exposed to different chlorhexidine delivery vehicles. J Endod 2000;26:652–5.
- Messer HH, Chen RS. The duration of effectiveness of root canal medicaments. J Endod 1984;10:240-5.
- Koontongkaew S, Silapichit R, Thaveboon B. Clinical and Laboratory assessments of camphorated monochlorphenol in endodontic therapy. Oral Surg Oral Med Oral Pathol 1988;65:757–62.
- Kraivaphan P, Koontongkaew S. The loss of camphorated monochlorphenol from the root canal: an in vitro study. J Dent Assoc Thai 1989;39:1–4.
- Stowe TJ, Sedgley CM, Stowe B, Fenno JC. The effects of chlorhexidine gluconate (0.12%) on the antimicrobial properties of tooth-colored ProRoot Mineral Trioxide Aggregate. J Endod 2004;30:429–31.
- Schaefer E, Boessmann K. Antimicrobial efficacy of chlorhexidine and two calcium hydroxide formulations against enterococcus faecalis. J Endod 2005;31:53–6.
- Abdullah M, Ng Y-L, Gulabivala K, Moles DR, Spratt DA. Susceptibilities of two enterococcus faecalis phenotypes to root canal medications. J Endod 2005;31:30-6.
- Schmalz G, Ergücü Z, Hiller K-A. Effect of dentin on the antibacterial activity of dentin bonding agents. J Endod 2004;30:352–8.
- Parsons GJ, Patterson SS, Miller CH, et al. Uptake and release of chlorhexidine by bovine pulp and dentin specimens and their subsequent acquisition of antibacterial properties. Oral Surg Oral Med Oral Pathol 1980;49:455–9.
- White RR, Hays GL, Janer LR. Residual antimicrobial activity after canal irrigation with chlorhexidine. J Endod 1997;23:229

  –31.
- Abbott PV. In vitro studies of the pharmacodynamics of the active components of Ledermix paste, a corticosteroid-antibiotic root canal dressing material. Thesis: Adelaide, Australia: University of Adelaide; 1985.